

## DECLARATION OF PERFORMANCE

Technical Specifications for laminate flooring FLOORPAN and ARTFLOOR

FLOORPAN	ARTFLOOR		CLASSIC	REGISTER	URBAN	SUN	DELUXE	STONE	BOUTIQUE	NATURAL	Test Method
Density		kg/m <sup>3</sup>	900 ± 30	900 ± 30	900 ± 30	900 ± 30	900 ± 30	920 ± 30	900 ± 30	880 ± 30	EN 323
Thickness		mm	8	8	8	8	8	8	8	10	EN 13329+A1
Width		mm	197	193	197	197	197	402	193	157	EN 13329+A1
Length		mm	1205	1295	1205	1205	1205	1206	1295	1205	EN 13329+A1
Class		-	31	32	32	31	32	33	33	32	EN 13329+A1
Abrasion resistance		-	AC3	AC4	AC4	AC3	AC4	AC5	AC5	AC4	EN 13329+A1
Thickness Swelling		%	≤ 18	≤ 18	≤ 18	≤ 18	≤ 18	≤ 15	≤ 15	≤ 18	ISO 24336
Resistance to impact	Small ball	N	≥ 8	≥ 12	≥ 12	≥ 8	≥ 12	≥ 15	≥ 15	≥ 12	EN 13329+A1
	Large ball	mm	≥ 500	≥ 750	≥ 750	≥ 500	≥ 750	≥ 1000	≥ 1000	≥ 750	EN 13329+A1
Warranty domestic / Commercial		years	10/5	15/10	15/10	10/5	15/10	30/15	25/15	15/10	
Resistance to staining			Not lower than 5 (groups 1 and 2) / Not lower than 4 (group 3)								EN 438
Surface Soundness		N/mm <sup>2</sup>	≥ 1.0	≥ 1.25	≥ 1.25	≥ 1.0	≥ 1.25	≥ 1.25	≥ 1.25	≥ 1.25	EN 13329+A1
Lock strength	Length	kN/m	-	f <sub>0,2</sub> ≥ 1	f <sub>0,2</sub> ≥ 1	-	f <sub>0,2</sub> ≥ 1	f <sub>0,2</sub> ≥ 1	f <sub>0,2</sub> ≥ 1	f <sub>0,2</sub> ≥ 1	ISO 24334
	Width	kN/m	-	f <sub>50,2</sub> ≥ 2	f <sub>50,2</sub> ≥ 2	-	f <sub>50,2</sub> ≥ 2	f <sub>50,2</sub> ≥ 2	f <sub>50,2</sub> ≥ 2	f <sub>50,2</sub> ≥ 2	
Effect of a castor chair	25.000 cycles		No Damage							EN 425-2002	
Effect of a furniture leg	-		No Damage							EN 424	
Opening between elements		mm	≤ 0,20							EN 13329+A1	
Height difference between elements		mm	≤ 0,15							EN 13329+A1	
Humidity		%	4-10							EN 322	
Formaldehyde emission		mg/m <sup>2</sup> h	≤ 3,5 (E1)							EN 12460-3	

**UNIFIT**®  
PATENTED TECHNOLOGY



**mikro**  
derzli

**CARB**<sub>12</sub>  
Compliant

